



Minimum Application Rates

T
E
C
H
N
I
C
A
L
B
U
L
L
E
T
I
N

Minimum Application Rates (Silicone)

Silicone 44 (High Solids): 20 wet mils
Silicone 22 (Low Solids): 32 wet mils

Minimum Application Rates (Acrylic)*

** Acrylic Coatings require a two coat system of base coat & finish coat*

Uniflex Premium White 41-300: 16 wet mils
Uniflex Premium Gray 41-320: 16 wet mils
Uniflex SPE Gray Basecoat 41-321: 16 wet mils
Uniflex MB Basecoat 41-510/512: 24 wet mils
Uniflex Elastomeric Tint Bases: 24 wet mils**

*** Multiple coats at lower rates may be required for darker colors or high temperatures*

Review Uniflex Specifications for actual rates required for warranties.

Note that rough or porous surfaces may require additional materials.