



Minimum Application Rates for 10 Year Material Warranties

See Specifications Additional Details

WARRANTY DOCUMENT

Roof Type	Coating Options	Primer	Seam Detail	Penetrations	Base Coat	Finish Coat
Metal	Acrylic Elastomeric Coating System	All rust must be primed with Rust Inhibitive Primer 34-520 @ 200 sq.ft./gal.	Seal all overlaps with 41-320 Gray Base coat @ 16 wet mils extending 2" on each side of the lap.	Seal all Penetrations with Uniflex One Flash @ 60 wet mils	Gray Elastomeric 41-320 @ 1 gal./square (16 wet mils)	White Elastomeric 41-300 @ 1.5 gal./square (24 wet mils)
	Silicone 44 Coating System	All rust must be primed with Rust Inhibitive Primer 34-520 @ 200 sq.ft./gal.	Seal all overlaps with Silicone 44 coating @ 16 wet mils extending 2" on each side of the lap.	Seal all Penetrations with Uniflex One Flash @ @60 wet mils	n/a	Silicone 44 @ 1.5 gal./square (24 wet mils)
Single-Ply	Acrylic Elastomeric Coating System	Bond-it-Wash Required for EPDM	Seal all field seams with SPE Base coat @ 16 wet mils extending 2" on each side of the lap.	Seal all penetrations with Uniflex One Flash @ 60 wet mils	SPE Gray Acrylic Base Coat 41-321 @ 1.5 gal./square (24 wet mils)	White Elastomeric 41-300 @ 1.5 gal./square (24 wet mils)
	Silicone 44 Coating System	Bond-it-Wash may be required for EPDM	No additional detailing required for tight field seams	Seal all penetrations with Uniflex One Flash @ 60 wet mils	n/a	Silicone 44 @ 1.5 gal./square (24 wet mils)
Asphalt Built Up Roof (BUR)	Acrylic Elastomeric Coating System	n/a	n/a	Seal all penetrations with Uniflex One Flash @ 60 wet mils	MB Base Coat 41-512 @ 1.5 gal./square (24 wet mils)	White Elastomeric 41-300 @ 1.5 gal./square (24 wet mils)
	Silicone 44 Coating System	Optional: Bleed Block Primer	n/a	Seal all penetrations with Uniflex One Flash @ 60 wet mils	n/a	Silicone 44 @ 1.5 gal./square (24 wet mils)
Modified Bitumen	Acrylic Elastomeric Coating System	n/a	Seal all field seams with MB Base coat @ 16 wet mils extending 2" on each side of the lap.	Seal all penetrations with Uniflex One Flash @ 60 wet mils	MB Base Coat 41-512 @ 1.5 gal./square (24 wet mils)	White Elastomeric 41-300 @ 1.5 gal./square (24 wet mils)
	Silicone 44 Coating System	Optional: Bleed Block Primer	No additional detailing required for tight field seams	Seal all penetrations with Uniflex One Flash @ 60 wet mils	n/a	Silicone 44 @ 1.5 gal./square (24 wet mils)

