



Uniflex Silicone Snapshot

Modified Bitumen



**P
R
E
P
A
R
E**

Conduct: *Moisture Survey & Adhesion Tests*
Repair: *Open Seams, Flashings, Damaged Membrane*
Replace: *Wet Insulation, Pitch Pan Sealants, Termination Sealants*
Clean: *Pressure Wash*
Apply: *Bleed Block Primer (Optional)*
Detail: *Uniflex One Flash*
Apply: *Uniflex Silicone 44 Finish-coat*

**A
P
P
L
Y**

OneFlash: *Detail all flashings and penetrations. Apply OneFlash at 60 wet mils, extending 2 inches on each side of the overlap seams.*

Primer: *Apply Uniflex Bleed Block Primer at 1 gallon per square (16 wet mils) to newer asphalt*

Basecoat: *Not Required*

Finishcoat *10 Year System: Apply Uniflex Silicone 44 at 2.0 gallons per square. (32 wet mils)*
15 Year System: Apply Uniflex Silicone 44 at 2.5 gallons per square (40 wet mils)
20 Year System: Apply Uniflex Silicone 44 at 3.0 gallons per square (48 wet mils)

**W
A
R
R
A
N
T
Y**



Ten or Fifteen Year Available

No Cost or Pre-Approval Required

Pre-Approval Required- Warranty Fee Required

Ten, Fifteen or Twenty Year Available

**L
I
N
K
S**

Uniflex Website
Uniflex Warranty
Full Specification
Roof Calculator

**P
R
O
D
U
C
T
S**

Uniflex Silicone 44 White Finish Coat
Uniflex One Flash
Uniflex Bleed Block Primer



Need a Moisture Survey?

Ask Your Uniflex Regional Manager about Uniflex Roof View Thermal Imaging
or click the image for additional information

NOTE: This Snapshot is not designed to replace the full system specification. Full specifications are available at www.uniflexroof.com/specifications. Contractor must be a Uniflex Approved Applicator for System Warranties.